

Ready Hand Plaster

Product Description

Cement-based, hand-applied general purpose plaster that performs the function of coarse and fine plaster together.

Areas of Use

Inside and outside of all structures.

Application Surfaces

It is applied to brick, bims, gross concrete, briquette wall surfaces both indoors and outdoors

Advantages

- It offers easy and fast application.
- It functions as coarse and fine plaster.
- With its homogeneous structure, it shows high adhesion and strength strengths at every point of the surface.

Preparation of the Surface

- The surface must be cleaned from mold oil, dust, paint and adherence reducing agents.
- Repair of cracks and holes before application must be done with Newkim repair mortar.
- If necessary, the application surface should be moistened with water.
- It should be used 72 hours before pre-sprinkling on gas concrete walls.
- Sprinkling plaster should be applied before application on bright surfaces, concrete walls and ceilings.

Preparation of Mortar

- Newkim ready hand plaster is mixed with the hand mixer (4-5 Lt. water, 25 Kg. bag) and applied with a trowel on the surface.
- Application thickness is made between 1 cm and 2.5 cm in one layer.
- If the thickness is more than 2.5 cm, the



second layer is applied at a maximum thickness of 2-2.5 cm after setting the first layer.

- Special aluminum profiles should be used for a smooth plaster application and corner profiles should be used to prevent corner breakings.
- Hand psater applied in horizontal stripes between 2 boards, after should be gauged with special aluminum gauge profiles.
- After the plaster has hardened sufficiently, the surface application is finished with the help of a damp sponge.

Application Limit

- Direct plastering should not be applied on metal and wood surfaces.
- It is not applied on plaster surfaces.
- It is not applied on old painted surface, ready colored plaster, siding, non-solid old plaster, asbestos cement or insulation panel surfaces that may be exposed to continuous humidity.

Application Requirements

- Ambient temperature is between +5 °C and +35 °C. Avoid application under strong wind or sun
- It should not be applied on surfaces that are frozen, melting or that are in danger of frost within 24 hours.
- Suitable plaster netting should be used at different material joints and at points where movement may be thought.
- No foreign material should be added to the prepared mixture.

Application Tools

Electric mixer, gauge, steel trowel

Warnings and Recommendations

Certainly foreign materials should not be

- added to the mortar.
 Before application, the mortar should be
- thoroughly mixed until it reaches a homogeneous consistency.
 After application, all tools used should be
- washed with water before drying.

Technical Information	Technical Information is relative to 55% (\pm 5 °C) relative humidity environment at 23 °C (\pm 2 °C).
Appearance	White and Gray
Powder	1,65 kg. / Lt. (±0.1)
Density	4-5 lt. water / 25 kg. Powder
Water Mixing Rate	3-5 minutes
Resting Time Pot Life	Approximately 2 hours
Full Drying Application	24 hours
Temperature	+5°C / +35°C
Application Thickness	10-50 mm
Application Single Layer Thi	ckness 25 mm. Max.
Time to Wait Between Laye	rs 1 day Min.
Usage Period of Mortar	Max. 2 hours





